

Patent Abstracts of Japan

PUBLICATION NUMBER : 01014901
PUBLICATION DATE : 19-01-89

APPLICATION DATE : 09-07-87
APPLICATION NUMBER : 62169672

APPLICANT : SUMITOMO BAKELITE CO LTD;

INVENTOR : FUJIWARA KAZUHIKO;

INT.CL. : H01F 1/02 C08L 33/06

TITLE : PLASTIC MAGNET COMPOSITION

ABSTRACT : PURPOSE: To easily fill ferromagnetic powder highly and to improve injection moldability by adding specific ratio of ethylene-ethylacrylate copolymer as a binder to the powder.

CONSTITUTION: Ferrite magnetic powder, samarium cobalt magnetic powder or neodymium-iron-boron magnetic powder made of $MO_6Fe_2O_3$ (where M is one or more of Ba, Sr, Cr, Mg, Zn and Pb) is exemplified as ferromagnetic powder. 7~30pts.wt. of ethylene-ethylacrylate copolymer is added as a binder to 100pts. wt. of the powder. If the copolymer is 7pts.wt. or less, its injection moldability is wrong, while if it exceeds 30pts.wt., the magnetic force of a molded product becomes low due to low content of the powder in a composition, and the composition cannot be used for a motor or the like.

COPYRIGHT: (C)1989,JPO&Japio